



VIETTEL GROUP
CAMPCHA CEMENT JOINT STOCK COMPANY
 Add: Km 6, QL 18A – Quang Hanh – Quang Ninh
 Tel: 0203 3721.996 Fax: 0203 3714.605
 Email: info@camphacement.vn
 Website: Http://www.camphacement.vn



CERTIFICATE OF QUALITY

CONFIRMING THE SPECIFICATION AND QUALITY OF THE COMMODITY WITH Australian Standard AS 3972 : 2010				
Product: High early strength cement (Type HE)		Silo/No: 1		
Importer:		Date of production: 08/04/2026		
Brands:		Date of testing: 10/04/2026		
TEST RESULTS				
No	DESCRIPTION OF TEST	METHOD OF TEST	SPECCIFICATION REQUIREMENTS AS 3972 - 2010	TEST RESULTS
1	Chemical Compositition CaO SiO2 Al2O3 Fe2O3 MgO SO3 Loss on Ignition Chloride Na2O equivalent	AS 2350.2 AS 2350.2 AS 2350.2 AS 2350.2 AS 2350.2 AS 2350.2 AS 2350.2 ASTM C114 AS 2350.2	N/R N/R N/R N/R N/R 3,5% Maximum N/R 0,1% Maximum N/R	% 63,68 20,82 5,36 3,18 1,42 2,15 3,16 0,03 0,66
2	Normal Consistency	AS 2350.3	N/R	% Water 27,8
3	Setting Times Initial set Final set	AS 2350.4	45 min Minimum 360 min Maximum	Minutes 110 190
4	Soundness	AS 2350.5	5 mm Maximum	1,6 mm
5	Fineness Surface Area 45µm Residue	AS 2350.8 AS 2350.9	N/R N/R	360 m²/kg 3,8 %
6	Compressive Strength 3 Days 7 Days 28 Days	AS 2350.11	Mpa Minimum 25 40 N/R	Mpa 36,2 48,6 58,8

TESTED BY

Nguyen Thi Phuong



CHECKED BY



Quang Hanh, May 14th, 2026
CAMPCHA CEMENT JOINT STOCK COMPANY
 (AS CEMENT FACTORY)



Nguyen Thi Phuong

Vu Viet Van

Deputy General Director
Ngô The Hung